

Listing of Claims:

This listing of claims will replace all prior versions, and listings, of claims in the application:

33. (New) A nonwoven composite, comprising:
a non-woven material;
a film layer adhered to said non-woven material, said film layer prepared from a blended composition comprising
a) an unsaturated block copolymer, and
b) a compatibilizer including a styrenic block copolymer, wherein said compatibilizer has a melt flow rate of about 20 g/10 min. or more.
34. (New) The composite of claim 33, wherein said compatibilizer contains styrene-butadiene-styrene, styrene-isopropene-styrene, or combinations thereof.
35. (New) The composite of claim 33, wherein said unsaturated block copolymer is a styrene-isoprene-styrene block copolymer.
36. (New) The composite of claim 33, wherein said unsaturated block copolymer is a styrene-butadiene-styrene block copolymer.
37. (New) The composite of claim 33, wherein said compatibilizer has a melt flow rate of about 30 g/10 min. or more.
38. (New) The composite of claim 33, wherein said compatibilizer has a melt flow rate of about 40 g/10 min. or more.
39. (New) The composite of claim 33 wherein said compatibilizer has a melt flow rate of from about 20 g/10 min. to about 50 g/10 min.

40. (New) The composite of claim 33, wherein said unsaturated block copolymer and said compatibilizer are present in a ratio from about 95:5 to about 80:20.

41. (New) The composite of claim 33, wherein said unsaturated block copolymer is a styrene-isoprene-styrene block copolymer and said compatibilizer is a styrene-butadiene-styrene block copolymer.

42. (New) The composite of claim 41, wherein said styrene-isoprene-styrene and styrene-butadiene-styrene are present in said blended composition in a ratio of about 2:1.

43. (New) The composite of claim 33, wherein said compatibilizer has a styrene content by weight of at least about ten percent.

44. (New) The composite of claim 33, wherein said compatibilizer has a styrene content by weight of at least about twenty percent.

45. (New) The composite of claim 33, wherein said compatibilizer has a styrene content by weight of at least about thirty percent.

46. (New) The composite of claim 33, wherein said compatibilizer has a styrene content by weight of at least forty percent.

47. (New) The composite of claim 33, wherein said nonwoven material comprises a necked, spunbond material.

48. (New) The composite of claim 33, wherein said nonwoven material comprises a corrugated, spunbond material.

49. (New) The composite of claim 33, wherein said nonwoven material comprises a meltblown material.

50. (New) The composite of claim 33, wherein said composite has a first cycle hysteresis value of less than about 70 percent.